

Cone Equivalent Temperatures (F)

Cone	Self Supporting Cones 1 3/4" mounting height						Large Cones				Small 15/16" Height	
	Regular			Iron Free			Regular		Iron Free		Regular	PCE
	Heating Rate (F/hour)						Heating Rate (F/hour)					
	27	108	270	27	108	270	108	270	108	270	540	270
022	1049	1087	1094				N/A	N/A			1166	
021	1076	1112	1143				N/A	N/A			1189	
020	1125	1159	1180				N/A	N/A			1231	
019	1213	1252	1283				1249	1279			1333	
018	1267	1319	1353				1314	1350			1386	
017	1301	1360	1405				1357	1402			1443	
016	1368	1422	1465				1416	1461			1517	
015	1382	1456	1504				1450	1501			1549	
014	1395	1485	1540				1485	1537			1598	
013	1485	1539	1582				1539	1578			1616	
012	1549	1582	1620				1576	1616			1652	
011	1575	1607	1641				1603	1638			1679	
010	1636	1657	1679	1600	1627	1639	1648	1675	1623	1636	1686	
09	1665	1688	1706	1650	1686	1702	1683	1702	1683	1699	1751	
08	1692	1728	1753	1695	1735	1755	1728	1749	1733	1751	1801	
07	1764	1789	1809	1747	1780	1800	1783	1805	1778	1796	1846	
06	1798	1828	1855	1776	1816	1828	1823	1852	1816	1825	1873	
05½	1839	1859	1877	1814	1854	1870	1854	1873	1852	1868	1909	
05	1870	1888	1911	1855	1899	1915	1886	1915	1890	1911	1944	
04	1915	1945	1971	1909	1942	1956	1940	1958	1940	1953	2008	
03	1960	1987	2019	1951	1990	1999	1987	2014	1989	1996	2068	
02	1972	2016	2052	1983	2021	2039	2014	2048	2016	2035	2098	
01	1999	2046	2080	2014	2053	2073	2043	2079	2052	2070	2152	
1	2028	2079	2109	2046	2082	2098	2077	2109	2079	2095	2163	
2	2034	2088	2127				2088	2124			2174	
3	2039	2106	2138	2066	2109	2124	2106	2134	2104	2120	2185	
4	2086	2124	2161				2120	2158			2208	
5	2118	2167	2205				2163	2201			2230	

5½	2133	2197	2237				2194	2233			N/A	
6	2165	2232	2269				2228	2266			2291	
7	2194	2262	2295				2259	2291			2307	
8	2212	2280	2320				2277	2316			2372	
9	2235	2300	2336				2295	2332			2403	
10	2284	2345	2381				2340	2377			2426	
11	2322	2361	2399				2359	2394			2437	
12	2345	2383	2419				2379	2419			2471	2439
13		2428	2458				2410	2455				2460
13½		2466	2493									
14		2489	2523				2530	2491				2548
14½		2527	2568									
15		2583	2602				2595	2608				2606
15½		2617	2633									
16		2655	2687				2651	2683				2716
17		2694	2709				2691	2705				2754
18		2736	2746				2732	2743				2772
19		2772	2786				2768	2782				2806
20		2811	2824				2808	2820				2847
21		2851	2860				2847	2856				2883
23		2890	2898				2887	2894				2921
26							2892	2921				2950
27							2937	2961				2984
28							2946	2971				2995
29							2955	2993				3018
30							2977	3009				3029
31							3022	3054				3061
31½							3063	3088				3090
32							3103	3123				3123
32½							3124	3146				3135
33							3150	3166				3169
34							3195	3198				3205
35							3243	3243				3245

36							3268	3265				3279
37												3308
38												3362
39												3389
40												3425
41												3578
42												3659

Source: *The Edward Orton Jr. Ceramic Foundation* (permission to reprint with credit)